



OLCESE  
FERRARI

*il filato italiano*

ARIA

# A R I A

Ne 17/1 - Nm 1/28000

75% Lana Merinos Extrafine / Merinos Extrafine Wool

25% Poliammide / Polyamide

4983  
Greggio  
RawWhite

5407  
A

4985  
A

5128  
A

4984  
A

4986  
B

5129  
B

5409  
A

5675  
B

Stock Service

# A R I A

№ 17/1 - Nm 1/26000

75% Lana Merinos Extrafine / Merinos Extrafine Wool

25% Poliammide / Polyamide



6238  
B



6273  
B



6246  
B



6240  
B



6275  
B



5191  
B



5134  
B



4987  
B



4988  
B

# A R I A

Ne 17/1 - Nm 1/28000

## COMPOSIZIONE

75% Lana Merinos Extrafine

25% Poliammide

## IMPIEGO

Tessitura ordito e trama

Maglieria circolare

## ATTENZIONI PARTICOLARI

I colori non sono solidi alla sovratintura ed al candeggio

Nella variante greggia il colore può subire variazioni nel tempo, inoltre non sono garantite le solidità che dipenderanno dai coloranti impiegati nella tintura successiva

## MINIMI

Colori **STOCK SERVICE**: minimo una scatola

Maggiorazione prezzo applicata a quantità inferiori alla scatola

## COMPOSITION

75% Merinos Extrafine Wool

25% Polyamide

## APPLICATION

Weaving warp and weft

Circular Knitting

## SPECIAL CARES

Fastness of colours is not sufficient for over dyeing and bleaching

Raw-white colour may change along the time, besides fastness are not guarantee and they will depend from dyestuffs used in the following dyeing

## MINIMUM

**STOCK SERVICE** colours: one box minimum

For quantity less than one box: extra charge

Other colours if not available: minimum order 100 Kgs

## INFORMAZIONI TECNICHE / TECHNICAL INFORMATION

SOLIDITÀ FASTNESS	ISO	SCARICO SU COTONE DISCHARGE ON COTTON	DEGRADO COLOR CHANGING
LAVAGGIO IN ACQUA 40° C WASHING AT 40° C	105-C06	4	4
LAVAGGIO A SECCO DRY CLEANING	105-D01	4	4
SUDORE ACIDO-ALCALINO ACID-ALKALINE PERSPIRATION	105-E04	4	4
SFREGAMENTO/RUBBING			
REATTIVI / ZOLFO A SECCO / DRY	105-X12	3 - 4	4
REATTIVI A UMIDO / WET		3 - 4	4
ZOLFO A UMIDO / WET		2 - 3	3
LUCE ARTIFICIALE ARTIFICIAL LIGHT	105-B02	-	3

Note: valori medi / average values



COTONIFICIO OLCESE FERRARI s.p.A.

Ufficio commerciale: Via Marzaghetta, 7 - 25030 Adro (BS) ITALY

Tel. +39 030 7458830 - fax +39 030 7458833

sales.office@olceseferrari.it - www.olceseferrari.it

OEKO-TEX®  
CONFIDENCE IN TEXTILES  
STANDARD 100  
951453.0 CENTROCOT  
Tested for harmful substances.  
www.oeko-tex.com/standard100

