



OLCESE
FERRARI

il filato italiano

CLEO

C L E O

№ 12/1 - Nm 1/20000

65% Viscose / Viscose

30% Poliestere / Polyester

5% Seta / Silk



4909
A



4908
A



6549
A



4912
A



4911
B



7197
A



4913
A



4910
A



4915
B



4917
B



4916
B



4914
A

C L E O

Ne 12/1 Nm 1/20000

COMPOSIZIONE

65% Viscosa

30% Poliestere

5% Seta

IMPIEGO

Tessitura ordito trama

Maglieria Circolare

ATTENZIONI PARTICOLARI

Filato bottonato: in MAGLIERIA usare su finzze adeguate.

I colori non sono solidi alla sovratintura ed al candeggio

MINIMI

Colori **STOCK SERVICE** : minimo una scatola

Maggiorazione prezzo applicata a quantità inferiori alla scatola

Altri colori: se non disponibili ordine minimo Kg 300

COMPOSITION

65% Viscose

30% Polyester

5% Silk

APPLICATION

Weaving warp and weft

Circular Knitting

SPECIAL CARES

Knoppy yarn: KNIT on adequate gauges.

Fastness of colours is not sufficient for overdyeing and bleaching

MINIMUM

STOCK SERVICE colours: one box minimum

For quantity less than one box: extra charge

Other colours if not available: minimum order 300 Kgs

INFORMAZIONI TECNICHE / TECHNICAL INFORMATION S

SOLIDITÀ FASTNESS	ISO	SCARICO SU COTONE DISCHARGE ON COTTON	DEGRADO COLOR CHANGING
LAVAGGIO IN ACQUA 40° C WASHING AT 40° C	105-C06	4	4
LAVAGGIO A SECCO DRY CLEANING	105-D01	4	4
SUDORE ACIDO-ALCALINO ACID-ALKALINE PERSPIRATION	105-E04	4	4
SFREGAMENTO/RUBBING REATTIVI / ZOLFO A SECCO / DRY REATTIVI A UMIDO / WET ZOLFO A UMIDO / WET	105-X12	3 - 4 3 - 4 2 - 3	4 4 3
LUCE ARTIFICIALE ARTIFICIAL LIGHT	105-B02	-	5

Note: valori medi / average values



COTONIFICIO OLCESE FERRARI S.p.A.

Ufficio commerciale: Via Marzaghetta, 7 - 25030 Adro [BS] ITALY

Tel. +39 030 7458830 - fax +39 030 7458833

sales.office@olceseferrari.it - www.olceseferrari.it

OEKO-TEX®

CONFIDENCE IN TEXTILES

STANDARD 100

9514S3.0 CENTROCOT

Tested for harmful substances

www.oeko-tex.com/standard100

