

T U A R E G

Crèpe

Ne 18/2 - Nm 2/30000

COMPOSIZIONE: 85% Viscosa - 15% Lino Superfine

IMPIEGO

Tessitura ordito e trama

ATTENZIONI PARTICOLARI

I colori non sono solidi alla sovratintura ed al candeggio

Nella variante greggia il colore può subire variazioni nel tempo, inoltre non sono garantite le solidità che dipenderanno dai coloranti impiegati nella tintura successiva

MINIMI

Colori **STOCK SERVICE**: minimo una scatola

Maggiorazione prezzo applicata a quantità inferiori alla scatola. Altri colori se non disponibili: ordine minimo Kg 300

COMPOSITION: 85% Viscose - 15% Superfine Flax

APPLICATION

Weaving warp and weft

SPECIAL CARES

Colour fastness is not sufficient for overdyeing and bleaching

Raw-white colour may change along the time, besides fastness are not guarantee and the will depend from dyestuffs used in the following dyeing

MINIMUM


STOCK SERVICE colours: one box minimum

For quantity less than one box: extra charge. Other colours if not available: minimum order 300 Kgs

INFORMAZIONI TECNICHE / TECHNICAL INFORMATION

SOLIDITÀ FASTNESS	ISO	SCARICO SU COTONE DISCHARGE ON COTTON	DEGRADO COLOR CHANGING
LAVAGGIO IN ACQUA 40°C WASHING AT 40°C	105-C06	4	4
LAVAGGIO A SECCO / DRY CLEANING	105-D01	4	4
SUDORE ACIDO-ALCALINO ACID-ALKALINE PERSPIRATION	105-E04	4	4
SFREGAMENTO/RUBBING REATTIVI, SECCO/DRY REATTIVI A UMIDO / WET	105-X12	3 - 4 3 - 4	4 4
LUCE ARTIFICIALE / ARTIFICIAL LIGHT	105-B02	—	4

NOTE: valori medi / average values



COTONIFICIO OLCESE FERRARI s.p.a.

Ufficio commerciale: Via Marzaghetta, 7 - 25030 Adro (BS) ITALY

Tel. +39 02 2671721 / 030 7458830 - Fax +39 02 26717233 / 030 7458833

info@olceseferrari.it - sales.office@olceseferrari.it

www.olceseferrari.it

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
951453.0 CENTROCOT

Tested for harmful substances
www.oeko-tex.com/standard100

